



TEST REPORT

Report No.: HX201406186

Applicant: TIANJIN HUAYUAN ZHENGXING RUBBER PRODUCTS CO., LTD.
Address: Zhangjiawo village, zhangjiawo town, xiqing district, tianjin, china

Report on the submitted sample(s) said to be:

Name: Bicycle tyre
Type/Model: 26 × 1.95
Material: Rubber
Buyer: Diedrich Filmer GmbH
Supplier: -----

Date of Receipt: Jul.11, 2014 Test period: Jul.11, 2014 – Jul.16, 2014

Test Request: Polycyclic Aromatic Hydrocarbons (PAHs) Content

Test Result: Please refer to following page(s).

Tested by Lambk. wang Reviewed by Kevin Ren Approved by Hailiao Wang

Seal of: 
GUANGZHOU GRG METROLOGY & TEST CO., LTD.
Issue date: Jul.16, 2014

This test report is responsible for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts. The test report is invalid without the official stamp of GUANGZHOU GRG METROLOGY & TEST CO., LTD. The test report is invalid if altered. Objections to the test report must be submitted to GUANGZHOU GRG METROLOGY & TEST CO., LTD. within 15 days.

GUANGZHOU GRG METROLOGY & TEST CO., LTD.

Address: 163 Pingyun Road West of Huangpu Avenue Tianhe District Guangzhou City, 510656, P. R. China
Tel: +86-020-66664900 FAX: +86-020-38698685 <http://www.grgtest.com>

TEST REPORT

Report No.: HX201406186

Sample Description

1. Black rubber bicycle tyre

Test results

Test method: ZEK01.4-08 - Testing and Validation of Polycyclic Aromatic Hydrocarbons (PAH) in the course of GS-Mark Certification

Test Item	CAS No.	Result	Unit	MDL
		1		
Naphthalene	91-20-3	2.9	mg/kg	0.2
Acenaphthylene	208-96-8	0.7	mg/kg	0.2
Acenaphthene	83-32-9	2.7	mg/kg	0.2
Fluorene	86-73-7	8.0	mg/kg	0.2
Phenanthrene	85-01-8	15.8	mg/kg	0.2
Anthracene	120-12-7	3.1	mg/kg	0.2
Fluoranthene	206-44-0	7.3	mg/kg	0.2
Pyrene	129-00-0	16.1	mg/kg	0.2
Benzo[a]anthracene	56-55-3	1.8	mg/kg	0.2
Chrysene	218-01-9	3.7	mg/kg	0.2
Benzo[b]fluoranthene and Benzo[j]fluoranthene	205-99-2 205-82-3	0.7	mg/kg	0.2
Benzo[k]fluoranthene	207-08-9			
Benzo[a]pyrene	50-32-8	0.6	mg/kg	0.2
Indeno[1,2,3-cd]pyrene	193-39-5	0.2	mg/kg	0.2
Dibenz[a,h]anthracene	53-70-3	0.3	mg/kg	0.2
Benzo[g,h,i]perylene	191-24-2	0.9	mg/kg	0.2
Benzo[e]pyrene	192-97-2	2.7	mg/kg	0.2
Sum of 18 PAHs	---	67.5	mg/kg	---

Remark: 1) mg/kg = ppm
2) MDL= Method Detection Limit

GUANGZHOU GRG METROLOGY & TEST CO., LTD.

Address: 163 Pingyun Road West of Huangpu Avenue Tianhe District Guangzhou City, 510656, P. R. China
Tel: +86-020-66664900 FAX: +86-020-38698685 <http://www.grgtest.com>

TEST REPORT

Report No.: HX201406186


Limit:

Parameter	Category 1	Category 2	Category 3
	Materials intended to be put in the mouth or materials of toys for children aged < 36 months with intended skin contact ²⁾	Materials not covered by category 1, with foreseeable skin contact for longer than 30 seconds (long-term skin contact)	Materials not covered by category 1 or 2 with foreseeable skin contact up to 30 seconds (short term skin contact)
Benzo[a]pyrene (mg/kg)	Not detectable (< 0.2) ¹⁾	1	20
Sum 18 PAHs (mg/kg)	Not detectable (< 0.2) ¹⁾	10	200

¹⁾ If the limits of category 1 are surpassed but the limits of category 2 still met, one may confirm the suitability of the tested material which intended to be put in the mouth by additional specific migration tests of PAH components based on DIN EN 1186ff and §64 LFGB 80.30-1. The conclusion of the migration test results must be made based on food law criteria.

²⁾ According to the regulations of the EK2.

Test Process for PAHs.



TEST REPORT

Report No.: HX201406186

Photo of Sample



-----End of Report-----

GUANGZHOU GRG METROLOGY & TEST CO., LTD.

Address: 163 Pingyun Road West of Huangpu Avenue Tianhe District Guangzhou City, 510656, P. R. China
Tel: +86-020-66664900 FAX: +86-020-38698685 <http://www.grgtest.com>